



# DURA♦SKRIM® 6BB, 6WB & 6WW

FOUR-LAYER REINFORCED EXTRUSION LAMINATE

PROPERTIES	TEST METHOD	DURA♦SKRIM 6BB		DURA♦SKRIM 6WB		DURA♦SKRIM 6WW	
		IMPERIAL	METRIC	IMPERIAL	METRIC	IMPERIAL	METRIC
APPEARANCE		Black/Black		White/Black		White/White	
THICKNESS, NOMINAL		6 mil	0.15 mm	6 mil	0.15 mm	6 mil	0.15 mm
WEIGHT		24 lbs/MSF 3.5 oz/yd <sup>2</sup>	117 g/m <sup>2</sup>	27 lbs/MSF 3.9 oz/yd <sup>2</sup>	132 g/m <sup>2</sup>	28 lbs/MSF 4.0 oz/yd <sup>2</sup>	137 g/m <sup>2</sup>
CONSTRUCTION		Extrusion laminated with scrim reinforcement					
<sup>2</sup> 1" TENSILE STRENGTH	ASTM D7003	60 lbf/in	105 N/cm	60 lbf/in	105 N/cm	60 lbf/in	105 N/cm
<sup>2</sup> ELONGATION AT FILM BREAK	ASTM D7003	500 %	500 %	500 %	500 %	500 %	500 %
<sup>2</sup> GRAB TENSILE	ASTM D7004	75 lbf	333 N	75 lbf	333 N	75 lbf	333 N
<sup>1</sup> TRAPEZOID TEAR	ASTM D4533	45 lbf	200 N	45 lbf	200 N	45 lbf	200 N
MULLEN BURST	ASTM D751	50 psi	345 kPa	50 psi	345 kPa	50 psi	345 kPa
MAXIMUM STATIC USE TEMPERATURE		180° F	82° C	180° F	82° C	180° F	82° C
MINIMUM STATIC USE TEMPERATURE		-70° F	-57° C	-70° F	-57° C	-70° F	-57° C
WVTR	ASTM E96 Procedure B	0.018 grains/(ft <sup>2</sup> -hr)	0.293 g/(m <sup>2</sup> -day)	0.018 grains/(ft <sup>2</sup> -hr)	0.293 g/(m <sup>2</sup> -day)	0.018 grains/(ft <sup>2</sup> -hr)	0.293 g/(m <sup>2</sup> -day)
PERM RATING	ASTM E96 Procedure B	0.042 Perms grains/(ft <sup>2</sup> -hr-in Hg)	0.028 Perms g/(24hr-m <sup>2</sup> -mm Hg)	0.042 Perms grains/(ft <sup>2</sup> -hr-in Hg)	0.028 Perms g/(24hr-m <sup>2</sup> -mm Hg)	0.042 Perms grains/(ft <sup>2</sup> -hr-in Hg)	0.028 Perms g/(24hr-m <sup>2</sup> -mm Hg)

<sup>1</sup> Tests are an average of diagonal directions.

<sup>2</sup> Tests are an average of primary reinforcement directions.

Hydraulic conductivity values are derived from permeability data.

R6BB, R6WW, and R6WB =  $3.21 \times 10^{-10}$  cm/sec.

DURA♦SKRIM® 6BB, 6WB & 6WW are four-layer reinforced extrusion laminates. The outer layers consist of a high-strength polyethylene. Carbon black in the 6BB and UV stabilizers in the 6WW increase longevity.



DURA♦SKRIM® 6BB, 6WB & 6WW are reinforced with a heavy-duty scrim laid in a diagonal pattern spaced 3/8" apart.

DURA♦SKRIM® 6WW meets or exceeds ASTM E-84 standard, Class "A" for surface burning characteristics of building materials.



Scan QR Code to download technical data sheets.

Note: To the best of our knowledge, unless otherwise stated, these are typical property values and are intended as guides only, not as specification limits. Chemical resistance, odor transmission, longevity as well as other performance criteria is not implied or given and actual testing must be performed for applicability in specific applications and/or conditions. VIAFLEX MAKES NO WARRANTIES AS TO THE FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability for resulting loss or damage. Limited Warranty available at [www.viaflex.com](http://www.viaflex.com)

J 5: @LZ-B7"

, &%K '5 [ cbei ]b GfYhGjci I : U`gZG8 ) +%\$(  
D\ . Z %ff \$) E' ' )! \$%+( ' ' H . Z %fj \$ \$E\* ' )! ' ( ) \*  
! `&\$&&VIAFLEX INC. 5 " f] \hg fygfj YX"

sales@viaflex.com  
www.viaflex.com



27-0022 09/22